
# Flame Resistant (Equivalent to UL-94 Standard V-0) FR Three-layer Polyurethane Tubing

# Series TRTU




•



#### How to measure the minimum bending radius


to sparks from arc welding, etc.



Bend the tube into the U-form at a temperature of 20°C. Fix one end and close loop gradually. Measure 2R when the deformed ratio of the tube diameter at bending reaches 5%.

#### Model

colour



### **Specifications**

Blue (BU)


Yellow (Y)

Green (G)

Fluid Note 1)		Air, Water			
Applicable fittings		FR one-touch fittings: Series KR-W2 Metal one-touch fittings: Series KQB2			
Max. operating pressure	At 20°C	0.8 MPa			
	At 40°C	0.65 MPa			
	At 60°C	0.5 MPa			
Burst pressure		Refer to the burst pressure characteristics curve.			
Min. bending radius (mm) Note 2)		50	60	70	80
Ambient and fluid temperature		-20 to +60°C Water: 0 to 40°C (No freezing)			
Material	Inner tube	Polyurethane			
	Middle layer	Aluminium laminated film			
	Outer layer	Polyolefin (Equivalent to UL-94 standard V-0)			

- Note 1) Applicable for general industrial water. Please consult with SMC if using for the other kind of fluid. Also, the surge pressure must be under the maximum operating pressure. If the surge pressure exceeds the maximum operating pressure, it will result in damage to fittings and tubes.
- Note 2) The minimum bending radius is the representative value measured as shown in the left figure. Allow extra length when piping since the tube may be bent if used under the minimum bending radius.
- Note 3) The colour of all inner tubes is black.

## **Burst Pressure Characteristics Curve and Operating Pressure**



#### **How to Order**

